

**ATTAR**

Advanced Technology Testing and Research

ATTAR TEST REPORT NUMBER: 12/5677.1

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025. Accreditation Number: 2735

14 February 2012

Total Pages: 1**DRY SLIP RESISTANCE**

Job No: M12/5677

Prepared for:	Chemeco Pty Ltd 17 Yale Drive EPPING VIC 3076		
Attention:	Mr Gary Agouridis		
Test Site:	ATTAR, Unit 1, 64 Bridge Road, Keysborough.		
Test Date:	14 February 2012		
Test Specimens, Size and Quantity:	Terrazzo tiles coated with Armor Plate sealer, 40x40 cm, 5 off supplied.		
Sampling and Direction of Test:	Sampling conducted by client. Test direction not applicable.		
Test Personnel:	Steven Potts		
Preparation:	Washed with water and methylated spirits then dried.		
Fixed/Unfixed:	Unfixed		
Air Temperature:	22°C		
Test Equipment:	Tortus Floor Friction Tester; Tortus Model Mk III (with integral printer), Serial No: 318.		
Test Standard:	AS/NZS 4586: 2004 Slip resistance classification of new pedestrian surface materials – Appendix B.		
Slider Rubber:	Slider 96 (Four S) Batch No. 37		
Classification Criteria:	Refer Appendix 1 – Classification Criteria, attached.		
Dynamic Coefficient of Friction	Run 1	Run 2	Mean Rounded to 0.05
	0.75	0.74	0.75
Classification:	F		

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTAR

Steven Potts
Slip & Engineering Technician
Approved Signatory

This report may not be reproduced except in its entirety.

Page 1 of 1